

Rubber Magnet Properties

橡膠磁鐵磁性能

	(BH)max		Br		Hcb		Hcj	
	Maximum Energy 最大磁能值		Remanence 剩磁		Coercive Force 矯頑力		Intrinsic Coercive Force 內稟矯頑力	
	MGOe	KJ/m ³	KGS	MT	KOe	KA/m	KOe	KA/m
Standard Energy 同性	0.5-0.7	4.0-5.6	1.5-1.7	150-170	1.2-1.4	95-111	1.9-2.0	151-159
High Energy 異性	1.3-1.6	10.4-12.8	2.3-2.6	230-260	2.1-2.3	167-183	2.4-3.5	191-278